

Haydite Sieve Analysis Report

B Hydraulic Press Brick Company

Brooklyn, IN

Date 2/26/2003

Customer

Wt per CF	42.0	damp loose
Wt per CY	1133	damp loose
Moisture	6.76%	
FM	5.53	

Type Inventory

Screen	Wt. (gm)	% Ret	% Cum	% Pass	ASTM C-331	Limit Check
3/8 in	26.41	4.78%	4.78%	95.22%	80-100	Okay
No4	373.77	67.58%	72.36%	27.64%	5-40	Okay
No8	109.87	19.87%	92.22%	7.78%	0-20	Okay
No16	15.37	2.78%	95.00%	5.00%	0-10	Okay
No30	4.29	0.78%	95.78%	4.22%		
No50	3.02	0.55%	96.33%	3.67%		
No100	3.17	0.57%	96.90%	3.10%		
Pan	17.16	3.10%	100.00%	0.00%		
Total	553.04	IntWt 592.40	DryWt 554.88	Residual 0.33%		.3% loss Limit

Note

