

Haydite Sieve Analysis Report

BX Hydraulic Press Brick Company

Brooklyn, IN

Date 2/26/2003

Customer

Wt per CF	51.1	damp loose
Wt per CY	1379	damp loose
Moisture	8.44%	
FM	3.58	

Type Inventory

Screen	Wt. (gm)	% Ret	% Cum	% Pass	ASTM C-331	Limit Check	
3/8 in	6.64	1.13%	1.13%	98.87%	90-100	Okay	
No4	98.61	16.81%	17.94%	82.06%	65-90	Okay	
No8	125.24	21.35%	39.29%	60.71%	35-65	Okay	
No16	109.77	18.71%	58.01%	41.99%			
No30	78.73	13.42%	71.43%	28.57%			
No50	60.95	10.39%	81.82%	18.18%	10-25	Okay	
No100	37.01	6.31%	88.13%	11.87%	5-15	Okay	
Pan	69.61	11.87%	100.00%	0.00%			
Total	586.56	IntWt	640.17	DryWt	590.32	Residual 0.64%	.3% loss Limit

Note

